

Cera-Mix SPECIAL

- Mixing ratio: 0.25 L of water to 1 kg SPECIAL.
- Can be worked for approx. 6 min.
- Hardens after approx. 10 min.
- Surface Hardness: over 300 N/mm².

Used for: reliefs, models and casts.

Place the mould on a flat surface. Add Cera-Mix SPECIAL to the water and allow the mixture to soak. Stir the mixture for approx. 1 min. to avoid air bubbles. Pour the liquid mixture into the mould from the center toward the edges in a thin stream until the bottom is covered, then continue with a slightly more thicker stream. Remove the casting from the mould after approx. 20 min. Place the casting onto a heat resistant surface, as Cera-Mix SPECIAL generates heat during hardening. Cera-Mix SPECIAL hardens in 8 hours and can then be painted with Plus Color craft paint.

KEEP DRY.